

HSAF Polypropylene (PP) Film

DESCRIPTION

HSAF is a co-extruded transparent polypropylene (PP) film that is heat sealable on both sides with an anti-fog one side and corona treatment on the other.

CHARACTERISTICS

- Excellent heat seal strength
- Excellent anti-fog properties
- Inhibits deterioration of packaged foods

FDA STATUS

Manufactured with materials compliant with FDA regulations.

COMPLIANCE

Please visit <u>https://www.transcendia.com/compliance</u> for more compliance information.

TECHNICAL DATA

| PROPERTIES | UNIT OF MEASURE | GAUGE | TEST METHOD |
|--------------------------|------------------------------|---------|------------------|
| Thickness | Gauge | 120 | Transcendia Test |
| Yield | in²/lb | 25,750 | Transcendia Test |
| Tensile Strength MD | psi | 19,913 | ASTM D882A |
| Tensile Strength TD | psi | 35,558 | ASTM D882A |
| Elongation at Break MD | % | 225 | ASTM D882A |
| Elongation at Break TD | % | 60 | ASTM D882A |
| CoF | Film/film | 0.3 | Transcendia Test |
| Surface Tension | Dyne | 38 | ASTM D2578 |
| Haze | % | 3.3 | ASTM D1003 |
| Seal Range | °F | 239-284 | 20 PSI x 1 sec |
| Gloss | % | 80 | ASTM D2457 |
| Water Vapor Transmission | g/100in ² /24hrs | 0.30 | ASTM E96 |
| Oxygen Transmission Rate | cc/100in ² /24hrs | 95 | ASTM D3985 |
| Shrinkage MD | % | 3.5 | ASTM D1204 |
| Shrinkage TD | % | 1.5 | ASTM D1204 |

*All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.