

## CPPHS2-F POLYPROPYLENE (PP) FILM

### DESCRIPTION

CPPHS2-F is a slip modified, 2-side heat sealable cast polypropylene film with good stiffness the material is well-suited for VFFS applications.

### CHARACTERISTICS

- Good sealing performance
- Good stiffness
- Good temperature resistance

### FDA STATUS

Manufactured with materials compliant with FDA regulations

### COMPLIANCE

Please visit [transcendia.com/compliance](http://transcendia.com/compliance) for more compliance information.

### TECHNICAL DATA

PROPERTIES		UNIT OF MEASURE	TYPICAL VALUES	TEST METHOD
Thickness		gauge	200	-
Yield		in <sup>2</sup> /lb.	15,400	-
Tensile Strength	MD	psi	6,500	ASTM D882
Tensile Strength	TD	psi	5,500	ASTM D882
Elongation at Break	MD	%	650	ASTM D882
Elongation at Break	TD	%	700	ASTM D882
Haze		%	2	ASTM D1003
Gloss (45°)		Gloss units	85	ASTM D2457
CoF, A/B (Dynamic)			0.18	ASTM D1894
Secant Modulus	MD	psi	110,000	ASTM D882
Secant Modulus	TD	psi	105,000	ASTM D882

\*All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

#### CORPORATE HEADQUARTERS

9201 W. Belmont Avenue | Franklin Park, IL 60131  
 USA 800.745.5802 | 847.678.1800 main | 847.233.0199 fax  
 CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax  
[TRANSCENDIA.COM](http://TRANSCENDIA.COM)