

HT0-F BIAXIALLY ORIENTED POLYPROPYLENE (BOPP) FILM

DESCRIPTION

HT0-F is a co-extruded, non-heat sealable, biaxially oriented polypropylene (BOPP) film with two untreated sides. Also available in 60, 70, 140, 160, 200 & 235 gauge.

CHARACTERISTICS

- Excellent machinability with superior bond strengths for lamination
- Excellent stiffness
- Non-sealable film with good slip properties
- High gloss with low haze with very good flatness

FDA STATUS

Manufactured with materials compliant with FDA regulations

COMPLIANCE

Please visit transcendia.com/compliance for more compliance information.

TECHNICAL DATA

| PROPERTIES | UNIT OF MEASURE | TYPICAL VALUES | | | | TEST METHOD |
|------------------------|--------------------|----------------|-----------|-----------|-----------|----------------|
| Thickness | gauge | 80 | 90 | 100 | 120 | - |
| Yield | in²/lb. | 38,700 | 35,000 | 31,400 | 25,700 | - |
| Tensile Strength MD | psi | 20,000 | 20,000 | 20,000 | 20,000 | ASTM D882 |
| Tensile Strength TD | psi | 32,000 | 32,000 | 32,000 | 32,000 | ASTM D882 |
| Elongation at Break MD | % | 140 | 140 | 140 | 140 | ASTM D882 |
| Elongation at Break TD | % | 60 | 60 | 60 | 60 | ASTM D882 |
| Haze | % | 1.5 - 3.0 | 1.5 - 3.0 | 1.5 - 3.0 | 1.5 - 3.0 | ASTM D1003- 61 |
| Heat Shrinkage MD | % | <5 | <5 | <5 | <5 | 5 min at 266°F |
| Heat Shrinkage TD | % | <3 | <3 | <3 | <3 | 5 min at 266°F |

CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax **TRANSCENDIA.COM**

^{*}All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.