

OPTICITE® 540 LABEL FILM

DESCRIPTION

Opticite 540 is a white label film for applications that require rigidity and moisture resistance.

CHARACTERISTICS

- Master roll sizes: 6 Inch ID x 19, 24 or 32 inch OD
- Width (150 – 350 gauge): 40 – 70 inches
- Width (400 – 700 gauge): 40 – 45 inches
- Corona Treatment: Treated Outside or Untreated
- Surface: Smooth satin finish

FDA STATUS

Manufactured with materials compliant with FDA regulations

COMPLIANCE

Please visit transcendia.com/compliance for more compliance information.

TECHNICAL DATA

PROPERTIES	UNIT OF MEASURE	PROPERTY VALUE									TEST METHOD
		150	200	250	260	300	400	500	600	700	
Thickness	gauge	150	200	250	260	300	400	500	600	700	TM 101384
Yield	in ² /lb	16,595	12,446	9,957	9,547	8,297	6,223	5,083	4,268	3,685	TM 101257
Tensile Strength (MD)	psi	7,000-9,000									TM 101305
Tensile Strength (TD)	psi	7,000-9,000									TM 101305
Elongation at Break (MD)	%	20 - 75									TM 101305
Elongation at Break (TD)	%	20 - 75									TM 101305
Opacity	%	80					85				TM 101756
Surface Energy	Dynes/cm	55 - 65									TM 101563

*All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

CORPORATE HEADQUARTERS

9201 W. Belmont Avenue | Franklin Park, IL 60131
 USA 800.745.5802 | 847.678.1800 main | 847.233.0199 fax
 CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax
TRANSCENDIA.COM

*All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

CORPORATE HEADQUARTERS

9201 W. Belmont Avenue | Franklin Park, IL 60131

USA 800.745.5802 | 847.678.1800 main | 847.233.0199 fax

CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax

TRANSCENDIA.COM

Revision Date: 1/5/2025

©2025 Transcendia Inc. All Rights Reserved