

## OPTICITE® SQUEEZE WHITE LABEL FILM

### DESCRIPTION

OPTICITE SQUEEZE WHITE LABEL FILM is a polyolefin film for pressure-sensitive label applications that require squeezability.

### CHARACTERISTICS

- Corona treated
- Formulated to bond to fully flexible bottles or containers
- Moisture resistant
- Stain resistant

### FDA STATUS

Manufactured with materials compliant with FDA regulations

### COMPLIANCE

Please visit [transcendia.com/compliance](http://transcendia.com/compliance) for more compliance information.

### TECHNICAL DATA

PROPERTIES		UNIT OF MEASURE	TYPICAL VALUES	TEST METHOD
Thickness		mil.	4	ASTM D374
Yield		in <sup>2</sup> /lb.	8090	ASTM D4321
Color			White	-
Gloss 60°, 3.5 mil <sup>2</sup>		-	45	ASTM D2457
Gloss 60°, 3.5 mil <sup>3</sup>			20	
Treatment – Outside Surface Only		Dyne/cm	55	ASTM D2578
Opacity		%	85	ASTM D589
Tensile Strength	MD	psi	3400	ASTM D882
Tensile Strength	TD	psi	1800	
Elongation at Break	MD	%	230	ASTM D882
Elongation at Break	TD	%	60	
1% Secant Modulus	MD	psi	90,000	ASTM D882
1% Secant Modulus	TD		50,000	

\*All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

#### CORPORATE HEADQUARTERS

9201 W. Belmont Avenue | Franklin Park, IL 60131  
 USA 800.745.5802 | 847.678.1800 main | 847.233.0199 fax  
 CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax  
[TRANSCENDIA.COM](http://TRANSCENDIA.COM)