

SARANEX™ 750

DESCRIPTION

Saranex 750 Coextruded Barrier Films are smooth films designed for fabrication into ostomy pouches.

CHARACTERISTICS

- Available in clear (translucent) and beige
- Sealable by heat and high radio frequency
- Excellent odor barrier
- Soft texture
- Moderate noise characteristics
- SARAN film core maintains barrier properties even in high humidity.
- Offer excellent combination of barrier to water vapor and oxygen.
- Available in all common slit widths
- All ostomy films produced by Transilwrap go through two independent inspections for pin holes and other unwanted characteristics.

FDA STATUS

Manufactured with materials compliant with FDA regulations

COMPLIANCE

Please visit transcendia.com/compliance for more compliance information.

TECHNICAL DATA

PROPERTIES	UNIT OF MEASURE	TYPICAL VALUE	TEST METHOD
Thickness, Cross Web	mil	2.78 - 3.23	TM 101384
Yield	in ² /lb.	8640 - 10040	TM 101257
Coefficient of Friction In-Out, >24 hr.	Kinetic	.20 - .40	TM 101345
OTR	cm ³ /100in. ² /24hr	1.20 max.	TM 101558
Ultimate Tensile Strength, MD	psi	3000 min.	TM 101305
Ultimate Tensile Strength, TD	psi	2500 min.	TM 101305
Ultimate Elongation, MD	%	350 min.	TM 101305
Ultimate Elongation, TD	%	400 min.	TM 101305

*All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

CORPORATE HEADQUARTERS

9201 W. Belmont Avenue | Franklin Park, IL 60131
 USA 800.745.5802 | 847.678.1800 main | 847.233.0199 fax
 CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax
[TRANSCENDIA.COM](https://transcendia.com)

Revision Date: 6/19/2024
 ©2024 Transcendia Inc. All Rights Reserved