

TRA150

DESCRIPTION

TRA150 is a monolayer film designed specifically for use in handling, storage, and compounding of dry and liquid pharmaceutical materials. It is available in multiple formats including single wound sheeting, continuous tube on a roll, perforated bags on a roll, or individually cut bags in a case.

CHARACTERISTICS

- Good clarity with excellent handling characteristics
- Composed of strictly virgin resin with USP <661.1> guidelines in mind

FDA STATUS

Manufactured with materials compliant with FDA regulations

COMPLIANCE

Please visit transcendia.com/compliance for more compliance information.

TECHNICAL DATA

PROPERTIES		UNIT OF MEASURE	TYPICAL VALUES	TEST METHOD
Density		g/cm ³	0.9295	ASTM D792
Melting Point		°C	109.95	ASTM E324
Tensile Strength at Yield	MD	psi	3725	ASTM D882
Tensile Strength at Yield	TD	psi	2927	ASTM D882
Tensile Strength at Break	MD	lb	14.4	ASTM D882
Tensile Strength at Break	TD	lb	10.48	ASTM D882
Elongation at Break	MD	%	539	ASTM D882
Elongation at Break	TD	%	736	ASTM D882
1% Secant Modulus	MD	psi	26145	ASTM D683
1% Secant Modulus	TD	psi	27405	ASTM D683

*All information, recommendations and suggestions contained herein, including, without limitations, stated values (collectively the "Information") shall be used only as a guide by Purchaser and not for specification or any other purpose. The Information does not constitute a warranty nor guaranty of any type whatsoever. Purchaser should independently determine the suitability of all material purchased and must confirm adaptability and other characteristics by conducting its own test. Transcendia shall have no liability as a result of any loss, expense, damage, cost or other injury which results from Purchaser's reliance on the Information.

CORPORATE HEADQUARTERS

9201 W. Belmont Avenue | Franklin Park, IL 60131
 USA 800.745.5802 | 847.678.1800 main | 847.233.0199 fax
 CAN 800.268.4108 | 416.292.6000 main | 416.292.7399 fax
[TRANSCENDIA.COM](https://transcendia.com)